

GREEN SYNTHESIZED CALCIUM OXIDE NANOPARTICLES AND ITS ANTIBACTERIAL NATURE EVALUATION

Kanumalla Raghu Kranti Kumar

Lecturer in Zoology, Dept of Zoology, Sri Vivekananda Degree College, Podili, A.P

1. Introduction

Technology must be miniaturized to nanoscale size materials to function in the twentieth century. Nanostructures are a scientific discipline that involves manipulating materials on a nanoscale level. Nanomaterials act like atoms because they have a larger surface area, enormous surface potential, and unique surface properties. These nanosized materials exhibit high surface by volume ratios compared to bulk materials. The physical characteristics of larger particles are stable, have less surface volume ratio, and limit their applicability in many disciplines. Because of their size, shape, and morphology, bulk materials exhibit improved and unique characteristics when manipulated at the nanoscale level. As an individual, they are helpful in various disciplines, including material science, photochemistry, medicine, and solar energy. Calcium oxide (CaO) finds wide used in cosmetics, medicine, waste remediation, destructive adsorbent, and catalyst. Chemical precipitation, hydrothermal, microemulsion, sol-gel, gas phase, microwave synthesis, and electrochemical methods have been described for CaO NPs synthesized and for other nanomaterials such as NiO, FeO, ZnO, Ag, and Au. Green method is significant for cost-effective, harmless, and eco-friendly than any other methods like chemical and physical. According to the literature, some of the



phytoremediation notions found in the plant extract may be related to nanomaterial production's chemical mechanism. Metal/metal oxide nanoparticles (NPs) are considered the best way for future generations to use everywhere within clinical care, consumer items, and

other industrial applications. The adsorption of CO₂, biomedical applications, gas sensing, and photocatalytic activity of CaO NPs have also gotten much attention.

Moringa oleifera plant, is a drumstick evergreen or deciduous tree of a single genus in the *Moringaceae* family; because of its numerous nutritional, medicinal, and industrial benefits, it is regarded as a “wonder tree.” It is a tiny, fast-growing ornamental tree found throughout Africa and Asia’s tropical areas. It is primarily appreciated for its edible parts as fruits, leaves oil, leaves, and flowers, and it is widely utilized in traditional medicine. According to a literature survey, the leaves have a high nutritional content, including vitamins, minerals, and amino acids used as an alternate source for dietary supplements and growth boosters. Because of their high coagulation properties, the *M. oleifera* seeds powder has traditionally been used for purification of water in many rural regions ; in coagulation studies, a slight reduction in the total bacterial count of the filtered water was found, with antibacterial and antioxidant effects, indicating that the seeds may contain antibiotic compounds. *Moringa* is said to offer a variety of therapeutic properties. Thus, the *M. oleifera* tree parts are used in traditional medicine to cure diarrhea, hypertension, and folk medicines. As a result, herbal plants used in medicine, also known as phytomedicine, are still reliable. Plant components function as cardiac stimulants and anticancer, antiulcer, antipyretic, and anti-inflammatory. The *M. oleifera* Plant also has anticancer, antimicrobial, antidiabetic, antibiotic, antihypertensive, antioxidant, hepatoprotective, and cholesterol-lowering effects .

Moringa oleifera plant.

Due to the more effective and environmentally friendly approach to the biosynthesis of CaO NPs, the utilization of plant leaves aqueous extracts will be a worthy scientific challenge. It is long been recognized that phytochemicals present in a plant material can function as a biological reduction on metal and metal oxide production, with flavonoid compounds being one of the most influential families of secondary metabolites in plant tissues for metal ion reduction. Depending on the kind of plant, most flavonoid compounds include ascorbic acid, phenolics, and carotenoids. “*M. oleifera* leaf has been reported to be a rich source of beta-carotene, protein, vitamin C, carotenoids, polyphenols, phenolic acids, flavonoids, alkaloids, glucosinolates, isothiocyanates, tannins, saponins, calcium, and potassium, as well as a good source of natural antioxidants, and thus improve the shelf life of fat-containing foods due to various antioxidant compounds such as ascorbic acid, flavonoids, phenolics, and carotenoids”. In recent research, *Moringa* leaf powder aqueous extracts have been used to make nanoparticles. This is the first time a shrub has been used for green nanoparticle deposition. We perform work for the biosynthesis of CaO nanoparticles with the employment of *Moringa oleifera* leaves aqueous extract secondary metabolite compounds and its study regarding antibacterial activity because there is still a lack of scientific reports on using the extract of *Moringa oleifera* (MO) leaves as a biologically reductive and capping agent on the biosynthesis of MO-CaO nanoparticles. Furthermore, the antibacterial activity outline of nanomaterial was investigated in contrast to bacterial fears, with the final result revealing that Gram-positive (G+) bacteria (*Escherichia coli*) are more vulnerable than Gram-negative (G-) bacteria at various concentrations.

2. Materials and Methods

2.1. Materials

Analytical grades with 98% of purity of calcium nitrate Ca (NO₃)₂·6H₂O and sodium hydroxide (NaOH) and deionized water grade-I (Extra pure) Charco Chemicals. *M.*

oleifera leaves are collected through the local farm in Nashik, Pimpalgaon (B), Maharashtra, India.

2.2. Preparation of *Moringa oleifera* Plant Leaves Powder

Fresh mature *Moringa* leaves were collected during the daytime from the local farm, removed the leaves and discarded the stems and stalks, and then thoroughly were washed with distilled water and followed with deionized water to remove the various impurities such as mud, dust particles, and unwanted material. The MO leaves were allowed to dry in the oven at 80°C for 2 hrs after drying and made powder using mortar and pestle, and leaves powder, was taken for MO-CaO NPs synthesis purposes.


2.3. Synthesis of Calcium Oxide Nanoparticles Using *M. oleifera* Leaves (MO-CaO NPs)

The 2 g MO leaves powder was boiled in deionized water for 25 min at 60°C. A light brown colored solution was formed during the boiling and cooled at room temperature (RT). After that, the brown-colored aqueous extract was filtered (Whatman No. 1), and the filtrate (stock solution) was stored in the refrigerator (2°C to 4°C) for further work. 20 mL MO plant aqueous extract was boiled at 50°C to 60°C using a magnetic stirrer. The temperature of the solution was reached at 50°C to 60°C; 2 g of calcium nitrate ($\text{Ca}(\text{NO}_3)_2 \cdot \text{H}_2\text{O}$) was added to maintain the basic nature of the aqueous extract solution by using a few drops of sodium hydroxide (2 M NaOH) solution. Then the mixture was boiled until it became a yellow-colored paste and filtered through filter paper, and the precipitate was transferred to a crucible and heated in a muffle furnace up to 400°C for 3 hrs to obtain the white powder; it is the MO-CaO NPs which were identified by the characterizations and used for various applications.

3. Results and Discussion

3.1. UV-Vis Absorption Spectroscopy Analysis

The absorption spectra of *M. oleifera* leaf aqueous extract and MO-CaO NPs with an absorption peak of about 280.5 nm and 323 nm, respectively. The leaf extracts bump at 250 nm to 300 nm; it could be the presence of polyphenolic bioactive compounds responsible for reducing calcium ions to CaO NPs. The UV-Vis spectra of MO-CaO were taken in the solid-state, with the substantial excitation binding energy at 25°C; MO-CaO NPs show exciton absorption at 323 nm. Demonstrating UV-Vis of MO-CaO NPs, it can be seen that the nanomaterial has a good absorption capacity in the visible region.



UV spectra of *M. oleifera* leaf aqueous extract and MO-CaO NPs.

3.1.1. Vibrational Properties

The aqueous extract of *MO* contains a lot of phytochemicals such as alkaloids, glycosides, phenols, tannins, saponins, glucosinolate, and flavonoids. These major bioactive components will act as capping and stabilizing agents and can be reduced from calcium metal salt (Ca^{2+}) precursors to CaO NPs. To further affirm the formation of the CaO NPs crystal structure, FT-IR spectroscopy. The strong IR band located at 534 cm^{-1} attributed to fundamental vibrations of CaO, confirming the formation of CaO NPs. The broad peak observed at 1062 cm^{-1} corresponds to the C-O stretching frequency of phytochemicals in the *Moringa oleifera* aqueous leaves extract. The peaks around 1382 cm^{-1} correspond to the O-H bend of flavonoids and polyphenols, confirming the presence of an aromatic group. The absorption peak appearing around 1442 and 3430 cm^{-1} could be correlated to adsorbed water's bending and stretching vibrations bands and the residual -OH group. The bioactive/biomolecules in leaf extract of *Moringa oleifera* are responsible for the capping, reducing, and stabilizing CaO NPs. To identify the nature of the MO extract, which was responsible for the reduction of calcium ions to form the CaO NPs, the aqueous extract of MO were investigated [30]; the major bioactive compounds, as shown in Scheme 1 in *Moringa oleifera* leaf aqueous extract, may be responsible for capping and reducing the nature of the CaO NPs.

3.2. FT-IR Analysis

For the MO-CaO NPs and *M. oleifera* leaf aqueous extract, IR measurements were performed at room temperature using the KBr technique in the wavenumber range (400 to 4000 cm^{-1}). The CaO bond bending vibration appears as a peak in the low energy area at 437.98 cm^{-1} . Ca-oxygen is responsible for the zone between (400 and 600) cm^{-1} . The stretching vibration of the -OH group is responsible for the prominent peak in the higher energy area at 3600 – 3450 cm^{-1} . At roughly 2933 – 2915 cm^{-1} , the -CH stretching vibration band appears, indicating the existence of an alkanes group. The amide I and amide III sections of proteins/enzymes are responsible for the peaks around 1620 – 1655 and 1150 – 1390 cm^{-1} . The presence of functional groups of alcohols, and a carboxylic acid, may be seen in the influential bands detected at 1120 – 1065 cm^{-1} C–O stretching vibration. The absorption bands at 3430 , 2918 , 1624 , 1442 , and 1062 cm^{-1} in the FT-IR spectra indicate the structure of *M. oleifera* in which high phytochemicals parameters caused these peaks, as shown in above Figure. As a result, water-soluble phenolic acid and flavonoid components are essential in the bioreduction process.

The interactions between reducing phenolic acids such as ascorbic, cardiac glycoside, gallic acid, and calcium ions can lead to MO-CaO NPs. The mechanism of CaO NPs stabilization by *M. oleifera* leaf extract ascorbic acids and green production of CaO NPs might entail the reduction of calcium nitrate ions, which can form intermediate complexes with phenolic -OH groups found in hydrolyzable tannins, which are then oxidized to quinone forms, resulting in calcium reduction to CaO NPs. However, the process is yet unknown and has to be investigated further.

3.3. X-Ray Diffraction Microscopy (XRD)

The XRD patterns show perceptible peaks of CaO NPs at 29.59° , 32.22° , 37.35° , 42.81° , 53.83° , 64.09° , and 67.34° , corresponding to (011), (111), (002), (012), (022), (113), and (222) planes of cubic system CaO NPs. The plane values of XRD patterns agree with CaO (lime, syn, JCPDS card No. 00-004-0777) with cubic crystal system and lattice parameters (\AA). All recorded peak intensities were characteristics of the cubic structure; the relatively high intensity of the (002) peak indicates anisotropic growth and implies a preferred

orientation of the crystallites. The stiff and narrow diffraction peaks suggest that the product is excellent crystalline. There is no shift in the diffraction peaks, and other crystalline impurities are not observable.

3.4.1. Antibacterial Activity

According to the minimal inhibitory concentration (MIC) method, *Escherichia coli* and *Staphylococcus aureus* were used as microorganisms in this study. Stock solutions of synthesized compounds were prepared in DMSO. Cultures were incubated in nutrient broth for 24 hrs at 37°C at 160 rpm. The turbidity of bacterial suspension was adjusted at a concentration of approximately 10^6 cells/ml. The microorganisms grown were spread on the nutrient agar medium plate, and then a well was prepared with the help of a good borer. Then 100 μ l of a synthesized compound of various concentrations was added to each well. After that, all plates were incubated at 37°C for 24 hrs in the incubator. The minimum inhibitor concentration was taken as the MIC value, at which no growth was observed.

4. Conclusion

Leaf powder extracts of the *Moringa oleifera* plant act as capping and reducing agents due to phytochemical parameters used to make CaO nanoparticles for this study. Still, the reaction mechanism and specific bioactive groups are unknown and must be investigated further. The use of nanoparticles made from leaf extracts is a promising alternative to the more conservative chemical method. Ultraviolet visible (UV-Vis), Fourier transform infrared resonance (FTIR), X-ray diffraction (XRD), and scanning electron microscopy-energy dispersive X-ray analysis (SEM-EDS) were used to examine the plant-mediated CaO NPs. Furthermore, using the minimal inhibitory concentration (MIC) method approach, this work investigated the antibacterial activities of the produced CaO nanoparticles in contrast to scientific and traditional concerns. Finally, CaO nanoparticles synthesized from *M. oleifera* leaf powder aqueous extract exhibited promising results in Gram-positive bacterial strains with severe inhibition areas of 19 mm, 20 mm, 22 mm, 23 mm, and 24 mm at various concentrations when employing a consistent quantity of CaO NPs.

References

1. B. Moyo, P. J. Masika, A. Hugo, and V. Muchenje, "Nutritional characterization of *Moringa (Moringa oleifera Lam.)* leaves," *African Journal of Biotechnology*, vol. 10, no. 60, pp. 12925–12933, 2011.
- A. Ndabigengesere, K. S. Narasiah, and B. G. Talbot, "Active agents and mechanism of coagulation of turbid waters using *Moringa oleifera*," *Water Research*, vol. 29, no. 2, pp. 703–710, 1995.
- A. A. Ezhilarasi, J. J. Vijaya, K. Kaviyarasu, M. Maaza, A. Ayeshamariam, and L. J. Kennedy, "Green synthesis of NiO nanoparticles using *Moringa oleifera* extract and their biomedical applications: cytotoxicity effect of nanoparticles against HT-29 cancer cells," *Journal of Photochemistry and Photobiology B: Biology*, vol. 164, pp. 352–360, 2016.
- U. Eilert, B. Wolters, and A. Nahrstedt, "The antibiotic principle of seeds of *Moringa oleifera* and *Moringa stenopetala*," *Planta Medica*, vol. 42, no. 5, pp. 55–61, 1981.
5. J. Shindano and C. Kasase, *Moringa (Moringa Oleifera): A Source of Food and Nutrition, Medicine and Industrial Products*, 2010.